



FGDP1000



Chain Information

Chain Capacity	Number of Sprockets	
	per ft of width	per m of width
0% - 25%	-	9
25% - 50%	-	11
50% - 75%	-	13
75% - 100%	-	17

Available Materials

Prefix	Chain Material	Standard Pin Material	Temperature						Chain Strength		Approximate Weight		FDA Approval
			Fahrenheit			Celsius			lbs/ft	N/m	lbs/ft ²	Kg/m ²	
			min	max dry	wet	min	max dry	wet					
Standard Materials													
XLG	Low Friction Green	Polypropylene	-40	180	150	-40	82	66	1,500	21,885	1.11	5.42	Yes

Regulatory Information

The Food and Drug Administration (FDA) accepts certain materials for direct food contact. FDA approved material is compliant to FDA 21 CFR § 177.

Rexnord, MCC, and MatTop are trademarks of Rexnord Corporation.

All rights reserved.

Additional Notes

Chain strength is listed at room temperature. NR = Not Recommended.

For additional material information, see material portfolio.

For chain width information see page MT - WIDTH - 1.

Open area = 40.0%.